

ZZ[®] 582 Fire Protection Joint Seal**Technical data sheet**

Trade name:	ZZ[®] 582 Fire Protection Joint Seal						
Description:	Compressible polyurethane-based joint seal tape with halogen-free flame retardants; intumescent.						
Implementation areas:	Elastic fire protection joint seal for smoke gas tight joints of third-party rail car modules or for separation from the outer shell						
Product group:	IN16 – Interior seals EX12 – exterior seals						
Certificates:	<ul style="list-style-type: none">• Classification report no. 17/1713, Currenta• Test report no. 17/0798, ASTM E 126• Test report no. 17/0910, ASTM E 662						
Requirement set:	R22, R23 according to EN 45545-2						
Hazard level:	HL1, HL2, HL3						
Colour:	Red-brown						
Content / nominal sizes:	<table border="1"><thead><tr><th>Blank sizes (Width x height x length) [mm]</th></tr></thead><tbody><tr><td>10 x 10 x 1000</td></tr><tr><td>20 x 20 x 1000</td></tr><tr><td>30 x 30 x 1000</td></tr><tr><td>40 x 40 x 1000</td></tr><tr><td>50 x 50 x 1000</td></tr></tbody></table>	Blank sizes (Width x height x length) [mm]	10 x 10 x 1000	20 x 20 x 1000	30 x 30 x 1000	40 x 40 x 1000	50 x 50 x 1000
Blank sizes (Width x height x length) [mm]							
10 x 10 x 1000							
20 x 20 x 1000							
30 x 30 x 1000							
40 x 40 x 1000							
50 x 50 x 1000							
Transport / storage:	Dry, protected from dust and only in the original packaging						
Storage temperature:	5 °C to 30 °C						
Bulk density:	$\rho \geq 240 \text{ kg/m}^3$ to 300 kg/m^3						
Safety notices:	Please observe the safety data sheet.						

Behaviour in the event of fire

Classification of the fire behaviour according to DIN EN 13501-1:	Class E
--	---------

ZZ[®] 582 Fire Protection Joint Seal

Expansion pressure:	No expansion pressure measurable	
Foaming factor:	1.6x to 4.5x Tested on samples at 450 °C for more than 25 minutes with superimposed load. The foaming factor is a laboratory characteristic value. The foaming behaviour in installed status depends on the existing boundary conditions.	
Smoke generation according to EN ISO 5659-2:	D _s max (-) = 57	
Burning behaviour (Oxygen index) according to ISO 4589-2:	OI = 69.9 %	
Conventional index of Toxicity according to NF X 70-100-1 /-2:	CIT _{NLP} = 0,30	
Surface flammability according to ASTM E 162:	Flame spread index I _s = 14.2	
Specific optical density of smoke according to ASTM E 662:	<u>Non-flaming mode</u> D _s (1.5) (-) = 34 D _s (4.0) (-) = 80	<u>Flaming mode</u> D _s (1.5) (-) = 36 D _s (4.0) (-) = 84

Physical construction material / product characteristics

The following specifications do not represent guaranteed product characteristics. They must, therefore, be regarded exclusively as information intended to serve as guideline values.

Thermal conductivity:	λ = 0.103 W/(m*K) Test standard: DIN EN 12667	
Surface resistance:	R ₀ = 2.39 x 10 ⁹ Ω Test standards: DIN EN 60079-0 (VDE 0170-1):2013-04 Section 7.4 including application of note 2 of Section 7.4.2, IEC 60079-0:2011 and modified + Cor.:2012, EN 60079-0:2012, EN 80079-36 and TRGS 727:2016-07-29	

ZZ® 582 Fire Protection Joint Seal

Hygiene, health and environmental protection

Indoor air hygiene

Requirements of AgBB Scheme 2015 are fulfilled
 Test standards: prEN 16516, ISO 16000-3, ISO 16000-6,
 ISO 16000-9

Test lab: eco-INSTITUT Germany GmbH, Cologne
 Date: 25/08/2017

	Result	Requirement	Requirements fulfilled
Emission rating			
Measurement after 3 days			
TVOC (C6 – C16)	0.008 mg/m ³	≤ 10 mg/m ³	✓
Carcinogens (EU Cat. 1A and 1B)	< 0.001 mg/m ³	≤ 0.01 mg/m ³	✓
Measurement after 28 days			
TVOC (C6 – C16)	0.014 mg/m ³	≤ 1 mg/m ³	✓
Σ SVOC (C16-C22)	< 0.005 mg/m ³	≤ 0.1 mg/m ³	✓
R (dimensionless)	0.02	≤ 1	✓
VOC without NIK	< 0.005 mg/m ³	≤ 0.1 mg/m ³	✓
Carcinogens	< 0.001 mg/m ³	≤ 0.001 mg/m ³	✓

VOC emission class

A+ in accordance with French decree no. 2011-321
 Test standards: ISO 16000-3, ISO 16000-6,
 ISO 16000-9, ISO 16000-11, ISO 16017-1

Microbial metabolisation:

Inert / fungistatic / bacteriostatic
 Test standard: DIN EN ISO 846

ZZ[®] 582 Fire Protection Joint Seal

Other product characteristics

Influence of coating materials and chemicals

The following paints and occasional, brief influence of chemicals do not cause any change in the technical fire protection properties:

Coating materials: Dispersion paint, alkyd resin paint, polyurethane acrylic lacquer, epoxy resin lacquer

Solvent/oil: Trichloroethylene, xylene, acetone, white spirit, butyl acetate, butanol, domestic fuel oil

Gaseous chemicals: Brief storage over concentrated ammonia solution

Comment: Environmental conditions with high humidity levels and/or some coating materials and chemicals can cause minor lightening of the colour.

Contact with metals and plastics

The surface consistency of aluminium, stainless steel, galvanised steel and plastics made of polyethylene and polyvinyl chloride is not negatively affected upon contact with "Fire Protection Joint Seal ZZ 582".

All the information in this leaflet is based on current technical knowledge and experience. Details on processing and application must be checked on a project-by-project basis due to the variety of possible influences.

If the application for which our products are used is subject to a government agency approval obligation, then the user is responsible for obtaining this approval. We would be pleased to respond to any enquires you might have.

The information in this document and declarations of Karl Zimmermann GmbH in conjunction with this document do not constitute any assumption of a guarantee. Guarantee declarations require the separate, express written declaration of Karl Zimmermann GmbH.

The conditions specified in this data sheet represent the characteristics of the delivery object, they do not represent any specific values. Specific values must be separately determined on a case-by-case basis.

We reserve the right to adapt the product to technical progress and to new developments.

In all other aspects we refer to our general terms and conditions.